



CARB Secondary Method Test Report

Client 3-558

Report# 22-SM-060

Parfino Plywood Factory
Parfino, Novgorod Regin, Russia

Purpose: ULEF Renewal
Methodology: Section 93120.9 (a) (2) from Title 17,
California Code of Regulations

Product Information

Description:	HWPW-VC FSF – Phenol Formaldehyde glue – Fenotam GR-326 T 34	Sampling by:	Sampled by client (Report Attached)
Surface Treatment:	Sanded	Packaging:	Wrapped in Plastic
Thickness:	12 mm	PFS TECO Specimen Code:	Unspecified
Sample size (received):	300 mm x 300 mm	Batch/Lot Number:	Unspecified
Number of specimens:	9	Date manufactured:	24 May 2022
		Date sampled:	25 May 2022

Summary of Results


Small Chamber Test #	Formaldehyde Emission		Average Emission
	Calculated	Final Reported	
22-SC-315	0.002 ppm	<0.01 ppm	<0.01 ppm
22-SC-316	0.004 ppm	<0.01 ppm	
22-SC-317	0.007 ppm	0.01 ppm	

Evaluation


Criteria: CARB Phase 2 emission limit = 0.05 ppm

Decision: **Passed**

Prepared by:


Conner O'Brion
Formaldehyde Lab Technician
12 July 2022

Authorized by:


Zhaozhen Bao, Ph. D.
Senior Scientist
12 July 2022